

Technical Data

PHOTOCAP® 15420P

PHOTOCAP® 15420P is an ultra fast cure EVA (ethylene vinyl acetate copolymer) photovoltaic encapsulating film material with improved curing kinetics and photo-thermal stability. The cure kinetics of PHOTOCAP 15420P are improved relative to fast-cure EVA PHOTOCAP 15295P, which allows for yet faster cycle time during photovoltaic cell encapsulation. PHOTOCAP 15420P was commercially introduced in 2002 and is now the PV industry standard low shrink, “ultra-fast curing” EVA encapsulant used worldwide.

PHOTOCAP 15420P can be used for all crystalline silicon photovoltaic module constructions, and for many thin film photovoltaic designs. PHOTOCAP 15420P is provided as rolled film ready for use in thermal lamination processes. The material is self-priming for adhesion to glass.

Properties	Test Method	Units	Condition	Results
	ASTM			
Physical Mechanical				
Tensile Strength	D638	MPa	23 °C, 250 mm/min elongation rate	18
Ultimate Elongation	D638	%	23 °C, 250 mm/min elongation rate	850
10% Secant Modulus	D638	MPa	23 °C, 250 mm/min elongation rate	9.9
Hardness	D2240	Shore A/D	23 °C	69 / 21
Adhesion to Glass	STR	N/cm	23 °C	70-90
MVTR	F1249	g/m ² /day	25 °C/100sccm flow, 100%RH	23
Water Absorption	D570	wt%	23 °C	< 0.1
Optical				
Optical Transmission	E424	%	23 °C, 0.46 mm thickness	92
UV Cutoff Wavelength	E424	nm	23 °C, 0.46 mm thickness	360
Refractive Index	D542	-	23 °C, 0.46 mm thickness	1.482
Electrical				
Volume Resistivity	D257	ohm cm	23 °C	>1 x 10 ¹⁴
Dielectric Strength	D149	kV/mm	23 °C, 500V/sec	24

Tests are made in accordance with the current issue of the ASTM, or other cited test method. Test data reported here are nominal values measured on extruded films, 0.5 mm thick, or compression molded sheets and test bars, which have been cured at 150 °C for 7 minutes with a laboratory press. Optical measurements made with glass-EVA coupons with high transmission solar glass.

STR Locations

Email: sales@STRSolar.com
Tel: 1 860 272 4235

STR – United States of America
10 Water Street
Enfield, CT. USA 06082

STR – Malaysia
Plot D20, Jalan Tanjung A/3
Port of Tanjung Pelepas
Gelang Patah, Johor, Malaysia 81560

STR - Spain
Parque Tech de Asturias, Parcela
36
Llanera, Asturias, España
33428

STR – China
Changkun Ind. Park No.26
Nanxin Road, Sha Jiabang
Changshu, Suzhou, China 215542

Technical Data
page 2

PHOTOCAP[®] 15420P

AGENCY APPROVALS:

PHOTOCAP 15420P is a UL listed product in category QIHE2 Photovoltaic Polymeric Materials. Please refer to UL file numbers E310488.

PRODUCT VARIATIONS:

Suffix	Release Paper	Shrinkage	Notes
15420P/UF	Yes	Zero	STR's User Friendly (UF) technology allows sheets to be cut closer to size, resulting in less voids and shifting of ribbon and cells
15420P/UFP	No	Minimal	Paperless UF option, resulting in minimal shrinkage
15420P/PL	No	Higher than UF or UFP	Possesses a greater tendency to shrink but perfectly acceptable for use

PROCESS GUIDELINES:

Vacuum Lamination Step		Heat Cure Cycle	
Nominal Temperature	145 - 150 °C	Platen Temperature	145 - 150 °C
Vacuum Range	< 60 mbar	Cure Time	8 min
Evacuation Time	4 min	Applied Bladder Pressure	910 mbar
EVA Melting Range Via DSC	60 - 70 °C	Target Temperature within the Encapsulant	140 °C
		Time Above the Target Temperature	> 3 min

Processing conditions shown here are a recommended starting point for a crystalline silicon photovoltaic module processed with a typical 2-step vacuum lamination system. Actual values required to achieve desired cure levels will depend on the specific PV module design and the lamination process used.

The temperature of the encapsulant should be at or above the EVA melting range before pressure is applied for the cure cycle. The encapsulant should reach the target temperature during the cure cycle, and should remain above that target temperature for the time shown. Temperatures within encapsulant should be periodically measured with embedded thermocouples to assess temperature uniformity of the laminator heating plate and the rate of heat transfer to the PV module. More information about how to laminate PV modules with PHOTOCAP encapsulants is available from STR.

All PHOTOCAP grades are based upon over 30 years of STR's commercial experience in the photovoltaic market.

For further information, please contact the nearest Specialized Technology Resources office or agent.

PHOTOCAP[®] is a registered trademark of Specialized Technology Resources, Inc. The data set forth above is believed to be accurate. It is for informational purposes only and is not to be used for specification purposes. Neither Specialized Technology Resources, Inc., nor any of its affiliates, makes any representation or warranty as to, and disclaims all liability for, the information herein. PHOTOCAP is to be used by technically skilled persons at their own discretion and risk.